

PCT


WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>5</sup> : A61L 31/00, A61F 2/00		A1	(11) International Publication Number: WO 94/19029 (43) International Publication Date: 1 September 1994 (01.09.94)
(21) International Application Number: PCT/US93/05775 (22) International Filing Date: 16 June 1993 (16.06.93) (30) Priority Data: 08/019,394 18 February 1993 (18.02.93) US (71) Applicant: W.L. GORE & ASSOCIATES, INC. [US/US]; 551 Paper Mill Road, P.O. Box 9206, Newark, DE 19714 (US). (72) Inventors: KRANZLER, Thane, L.; 2650 N. Nelson Drive, Flagstaff, AZ 86001 (US). MCDONALD, Michael, L.; 6050 Townsend Winona Road, Flagstaff, AZ 86004 (US). (74) Agents: SAMUELS, Gary, A. et al.; W.L. Gore & Associates, Inc., 551 Paper Mill Road, P.O. Box 9206, Newark, DE 19714 (US).			(81) Designated States: CA, DE, GB, JP, SE, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).  Published With international search report.

(54) Title: A LAMINATED PATCH TISSUE REPAIR SHEET MATERIAL



(57) Abstract

A sheet of implantable patch tissue repair material having the form of a layer of porous polytetrafluoroethylene sheet material laminated to a layer of mesh-type sheet material having a multiplicity of openings through the mesh-type sheet material, said openings having a mean minimum diameter of about 0.1 mm. The inventive patch tissue repair material offers good strength characteristics, good biocompatibility, suture retention, and flexibility.

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

## A Laminated Patch Tissue Repair Sheet Material

### FIELD OF THE INVENTION

This invention relates to the field of implantable sheet materials useful for the repair of living tissue and particularly for hernia repairs.

### BACKGROUND OF THE INVENTION

Implantable sheet materials for tissue repair are well known. Tissue defects commonly repaired with these materials include wounds of the abdominal wall and in particular hernia repairs. Wounds of the chest wall, diaphragm and other weaknesses of the musculoaponeurotic tissues are also repaired with these materials.

There are two fundamental types of sheet materials that are most predominantly used. The first type is a mesh material having a multiplicity of openings through the material, such as Marlex® Mesh available from C. R. Bard, Inc., Billerica, MA. This is an open mesh knitted from polypropylene monofilament of about 0.17 mm diameter and having openings of about 0.54 mm diameter. These mesh materials offer good suture retention, good mechanical strength, and allow tissue to grow through the mesh openings.

An alternative type of implantable sheet material for tissue repair is GORE-TEX® Soft Tissue Patch made from porous expanded polytetrafluoroethylene, available from W. L. Gore & Associates, Inc., Flagstaff, AZ in 1.0 and 2.0 mm thicknesses. This is a porous sheet material that does not contain large, macroporous holes in the fashion of a mesh. Because there are no large holes for tissue to grow through and around, this material is useful when it is desirable to minimize the risk of tissue adhesion.

### SUMMARY OF THE INVENTION

5 The present invention is a sheet of implantable patch tissue repair material comprising a layer of porous polytetrafluoroethylene sheet material laminated to a layer of mesh-type sheet material having a multiplicity of macroporous openings through the mesh-type sheet material, said openings having a mean minimum diameter of about 0.1 mm. The inventive patch tissue repair material offers good strength characteristics, good biocompatibility, suture retention, and flexibility.

10 The term laminated is used herein to describe the bonding together of two layers of material in any fashion that prevents subsequent separation of the layers during ordinary use. Macroporous openings are herein considered to be openings visible to the human eye without magnification, and visibly open through the thickness of the layer through which the openings have been formed. Microporous  
15 openings require the use of magnification to make them visible to the human eye.

### BRIEF DESCRIPTION OF THE DRAWINGS

20 Figure 1 describes a perspective view of the laminated patch tissue repair sheet material of the present invention.

Figure 2 describes a cross section of the laminated patch tissue repair sheet material of the present invention.

### DETAILED DESCRIPTION OF THE INVENTION

25 Figure 1 shows a perspective view of the laminated patch tissue repair sheet material of the present invention having a layer 11 of porous PTFE laminated to a layer 13 of mesh-type sheet material having a multiplicity of openings through the mesh-type sheet material. Figure 2 describes a cross section of the laminated patch tissue repair sheet material.

The openings through the mesh-type sheet material should be of at least about 0.1 mm diameter. The general shape of the opening is not believed to be of any biological importance and can therefore be round, elliptical, triangular, square, rectangular, hexagonal, etc.

5 For non-circular openings having a length or long diameter and a width or short diameter, the term minimum diameter is defined herein as the maximum dimension, measured substantially parallel to the surface of the sheet material, that describes the width or short diameter of the non-circular opening. The minimum diameter is to be measured with the  
10 sample in a relaxed state with no deforming force. The mean minimum diameter is determined by randomly selecting a sample area containing at least 10 macroscopic openings, locating and measuring the minimum diameter of the ten largest openings within that area and calculating the mean diameter of those ten openings. If it is not possible to  
15 obtain a sample containing at least ten openings, then all openings within the area of the largest sample obtainable should be included in the calculation of the mean value.

The layer 13 of the mesh-type sheet material may be any suitable biocompatible material including polypropylene, polyethylene  
20 terephthalate, PTFE or microporous PTFE. The mesh-type sheet material may be in the form of a sheet from which the openings 15 have been cut or otherwise formed, or alternatively may be an open fabric such as a knit or a weave having a multiplicity of openings formed by widely spaced strands of the fabric.

25 The layer 11 of microporous PTFE is preferably microporous expanded PTFE made according to the teachings of U. S. Patents 3,953,566 and 4,187,390. This material has a microstructure of nodes interconnected by fibrils. It may also be made according to U.S. Patents 4,482,516 and 4,598,011 if a high strength material with a  
30 coarse microstructure is desired. Layer 11 may optionally be made as a laminate of multiple layers as taught by U.S. Patents 4,385,093 and 4,478,665.

Layers 11 and 13 may be laminated by at least two different methods. First, adhesives may be used to adhere the two layers. One  
35 such suitable adhesive is Silastic® Medical Adhesive Silicone Type A (Catalog no. 891) from Dow Corning, Midland, MI. A thermoplastic

adhesive such as Teflon FEP 120 Aqueous Dispersion from E. I. DuPont de Nemours, Wilmington, DE may be used. A coating of the FEP dispersion is applied to the side of the mesh-type layer 13 which is intended to be adhered to the porous PTFE layer 11. The two layers  
5 are then adhered by the application of heat and pressure (as for example applied by opposing rollers) with enough heat applied to cause melting of the Teflon FEP 120 Dispersion, about 290°C.

Alternatively, layers 11 and 13 may be laminated by the use of heat and pressure without the use of an additional adhesive. This has  
10 been found to be the preferred method when the mesh-type layer 13 of a material having a lower melting point than that of the porous PTFE layer 11. For example, when a layer 13 of mesh-type polypropylene is used, it was found that heating the polypropylene layer to about 180°C, which is in excess of the melting point of polypropylene, while  
15 simultaneously applying pressure in a direction perpendicular to the planes of layers 11 and 13 resulted in good adhesion between the two layers.

It was also found possible to form both layers 11 and 13 from porous expanded PTFE sheet materials. A sheet of 1 mm thick GORE-TEX  
20 Soft Tissue Patch material of about 6 cm x 6 cm, was used for the mesh layer 13 by forming holes 15 through the layer 13 by using a round punch of about 3 mm diameter. The holes were spaced about 1.2 cm apart. Layer 13 was then laminated with the use of heat and pressure to a second layer 11 of GORE-TEX Soft Tissue Patch material wherein  
25 layer 11 contained no holes. Lamination was accomplished by placing layers 11 and 13 between two plates heated to 380°C and applying about 1.3 kg/cm<sup>2</sup> pressure to the two layers. The heated plates were allowed to cool to about 300°C while the pressure was maintained. At the end of this time the pressure was released and the two laminated layers 11  
30 and 13 of porous expanded PTFE were removed. Laminated layers 11 and 13 were found to be well adhered in that repeated flexing of the laminated layers showed no inclination of the layers to separate.

## We Claim:

1. A sheet of implantable patch tissue repair material comprising a layer of porous polytetrafluoroethylene sheet material laminated to a layer of mesh-type sheet material having a multiplicity of openings through the mesh-type sheet material, said openings having a mean minimum diameter of about 0.1 mm.
2. A sheet of implantable patch tissue repair material according to claim 1 having a mean minimum diameter of about 0.2 mm.
3. A sheet of implantable patch tissue repair material according to claim 1 having a mean minimum diameter of about 0.4 mm.
4. A sheet of implantable patch tissue repair material according to claim 1 having a mean minimum diameter of about 0.6 mm.
5. A sheet of implantable patch tissue repair material according to claim 1 wherein the mesh-type sheet material is comprised of polypropylene.
6. A sheet of implantable patch tissue repair material according to claim 1 wherein the mesh-type sheet material is comprised of polyethylene terephthalate.
7. A sheet of implantable patch tissue repair material according to claim 1 wherein the mesh-type sheet material is comprised of polytetrafluoroethylene.
8. A sheet of implantable patch tissue repair material according to claim 7 wherein the polytetrafluoroethylene is porous polytetrafluoroethylene.
9. A sheet of implantable patch tissue repair material according to claim 1 wherein the layer of porous polytetrafluoroethylene comprises porous expanded polytetrafluoroethylene having a microstructure of nodes interconnected by fibrils.
10. A sheet of implantable patch tissue repair material according to claim 9 wherein the mesh-type sheet material is comprised of polypropylene.
11. A sheet of implantable patch tissue repair material according to claim 9 wherein the mesh-type sheet material is comprised of polytetrafluoroethylene.
12. A sheet of implantable patch tissue repair material according to claim 9 wherein the mesh-type sheet material is comprised of polyethylene terephthalate.

13. A sheet of implantable patch tissue repair material according to claim 11 wherein the polytetrafluoroethylene is porous polytetrafluoroethylene.
- 5 14. A sheet of implantable patch tissue repair material according to claim 1 wherein the layer of porous polytetrafluoroethylene is laminated to the layer of mesh-type sheet material by an adhesive.
- 15 15. A sheet of implantable patch tissue repair material according to claim 14 wherein the adhesive is silicone adhesive.
- 10 16. A sheet of implantable patch tissue repair material according to claim 14 wherein the adhesive is a fluoropolymer adhesive.
17. A sheet of implantable patch tissue repair material according to claim 14 wherein the adhesive is a fluorinated ethylene propylene adhesive.
- 15 18. A sheet of implantable patch tissue repair material according to claim 14 wherein the adhesive is a thermoplastic adhesive.
19. A sheet of implantable patch tissue repair material according to claim 1 wherein the layer of porous polytetrafluoroethylene is laminated to the layer of mesh-type sheet material by thermal  
20 bonding.






FIG. 1




FIG. 2

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 93/05775

<b>I. CLASSIFICATION OF SUBJECT MATTER</b> (If several classification symbols apply, indicate all) <sup>6</sup> According to International Patent Classification (IPC) or to both National Classification and IPC Int.Cl. 5 A61L31/00;                      A61F2/00											
<b>II. FIELDS SEARCHED</b> <div style="text-align: center; margin-top: 5px;">Minimum Documentation Searched<sup>7</sup></div> <table border="1" style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 30%; padding: 5px;">Classification System</td> <td style="padding: 5px;">Classification Symbols</td> </tr> <tr> <td style="padding: 5px;">Int.Cl. 5</td> <td style="padding: 5px;">A61L ;              A61F</td> </tr> </table> <div style="text-align: center; margin-top: 5px;">Documentation Searched other than Minimum Documentation to the Extent that such Documents are included in the Fields Searched<sup>8</sup></div>			Classification System	Classification Symbols	Int.Cl. 5	A61L ;              A61F					
Classification System	Classification Symbols										
Int.Cl. 5	A61L ;              A61F										
<b>III. DOCUMENTS CONSIDERED TO BE RELEVANT<sup>9</sup></b> <table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th style="width: 10%; padding: 5px;">Category<sup>10</sup></th> <th style="width: 70%; padding: 5px;">Citation of Document, <sup>11</sup> with indication, where appropriate, of the relevant passages <sup>12</sup></th> <th style="width: 20%; padding: 5px;">Relevant to Claim No.<sup>13</sup></th> </tr> </thead> <tbody> <tr> <td style="text-align: center; vertical-align: top; padding: 5px;">A</td> <td style="padding: 5px;">WO,A,9 210 218 (GORE) 25 June 1992</td> <td></td> </tr> <tr> <td style="text-align: center; vertical-align: top; padding: 5px;">A</td> <td style="padding: 5px;">US,A,3 124 136 (USHER F.C.) 10 March 1964</td> <td></td> </tr> </tbody> </table> <div style="display: flex; justify-content: space-between; margin-top: 10px;"> <div style="width: 48%;"> <p><sup>10</sup> Special categories of cited documents: <sup>10</sup></p> <p>"A" document defining the general state of the art which is not considered to be of particular relevance</p> <p>"E" earlier document but published on or after the international filing date</p> <p>"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)</p> <p>"O" document referring to an oral disclosure, use, exhibition or other means</p> <p>"P" document published prior to the international filing date but later than the priority date claimed</p> </div> <div style="width: 48%;"> <p>"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention</p> <p>"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step</p> <p>"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.</p> <p>"A" document member of the same patent family</p> </div> </div>			Category <sup>10</sup>	Citation of Document, <sup>11</sup> with indication, where appropriate, of the relevant passages <sup>12</sup>	Relevant to Claim No. <sup>13</sup>	A	WO,A,9 210 218 (GORE) 25 June 1992		A	US,A,3 124 136 (USHER F.C.) 10 March 1964	
Category <sup>10</sup>	Citation of Document, <sup>11</sup> with indication, where appropriate, of the relevant passages <sup>12</sup>	Relevant to Claim No. <sup>13</sup>									
A	WO,A,9 210 218 (GORE) 25 June 1992										
A	US,A,3 124 136 (USHER F.C.) 10 March 1964										
<b>IV. CERTIFICATION</b> <table border="1" style="width: 100%; border-collapse: collapse;"> <tr> <td style="width: 50%; padding: 5px;">           Date of the Actual Completion of the International Search  <div style="text-align: center; margin-top: 5px;">15 OCTOBER 1993</div> </td> <td style="width: 50%; padding: 5px;">           Date of Mailing of this International Search Report  <div style="text-align: center; margin-top: 5px;">22 10. 93</div> </td> </tr> <tr> <td style="padding: 5px;">           International Searching Authority  <div style="text-align: center; margin-top: 5px;">EUROPEAN PATENT OFFICE</div> </td> <td style="padding: 5px;">           Signature of Authorized Officer  <div style="text-align: center; margin-top: 5px;">PELTRE CHR.</div> </td> </tr> </table>			Date of the Actual Completion of the International Search <div style="text-align: center; margin-top: 5px;">15 OCTOBER 1993</div>	Date of Mailing of this International Search Report <div style="text-align: center; margin-top: 5px;">22 10. 93</div>	International Searching Authority <div style="text-align: center; margin-top: 5px;">EUROPEAN PATENT OFFICE</div>	Signature of Authorized Officer <div style="text-align: center; margin-top: 5px;">PELTRE CHR.</div>					
Date of the Actual Completion of the International Search <div style="text-align: center; margin-top: 5px;">15 OCTOBER 1993</div>	Date of Mailing of this International Search Report <div style="text-align: center; margin-top: 5px;">22 10. 93</div>										
International Searching Authority <div style="text-align: center; margin-top: 5px;">EUROPEAN PATENT OFFICE</div>	Signature of Authorized Officer <div style="text-align: center; margin-top: 5px;">PELTRE CHR.</div>										

**ANNEX TO THE INTERNATIONAL SEARCH REPORT  
ON INTERNATIONAL PATENT APPLICATION NO.**

US 9305775  
SA 76383

This annex lists the patent family members relating to the patent documents cited in the above-mentioned international search report.  
The members are as contained in the European Patent Office EDP file on  
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information. 15/10/93

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO-A-9210218	25-06-92	EP-A- 0560934	22-09-93
US-A-3124136		None	

EPO FORM P0679

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82